

SODIUM ALUMINOSILICATE [Zeolite 4A]

(CAS: 1318-02-1)

Ca ion exchange capacity (dry) MgCaCO₃ / g	:	≥ 310
pH value	:	≤ 11
Ignition loss (800 °C, 60 min)	:	≤ 22%
Al 3+ content	:	≥ 18%
Whiteness	:	≥ 95
Density	:	0.38 - 0.45
Particle size D50	:	2 - 6 μm
Angle of repose	:	62° - 64°
325 mesh sieve residue	:	≤ 1