

ZINC STEARATE

(CAS: 557-05-1)

Grade	Appearance	Metal Content %	Ash Content %	Free Fatty Acid %	Moisture %	Melting Point °C	Bulk Density g/l
Grade 1	White Powder	10.4 - 11.2	13.0 - 14.0	0.50 max.	0.50 max.	118 - 125	200 - 300
Grade 2	White Powder	10.4 - 11.2	13.0 - 14.0	1.00 max.	1.00 max.	118 - 123	200 - 300
Grade 3	White Granules	10.4 - 11.2	13.0 - 14.0	1.00 max.	1.00 max.	118 - 123	450 - 600
Grade 4	White Powder	10.4 - 11.2	13.0 - 14.0	1.00 max.	1.00 max.	118 - 123	450 - 600
Grade 5	White Powder	10.2 - 11.0	12.8 - 13.8	0.50 max.	0.50 max.	118 - 123	170 - 200
Grade 6	White Powder	7.8 - 8.7	9.8 - 10.8	1.00 max.	1.00 max.	118 - 123	250 - 350
Grade 7	White Powder	10.4 - 11.2	13.2 - 14.0	1.00 max.	0.50 max.	120 - 122	160 - 240